



HYDROGRIP

PRODUCT DESCRIPTION

Inodorous fast drying primer. Matt appearance. Appropriate for building but is especially suitable for indoor and outdoor industrial work.

Can be applied to metal, galvan, aluminum, stainless steel, stone, tiles, glass, MDF, plastic and solvent paint where it shows very good toughness and good adhesion.

COMPOSITION

Acrylic resin 100% water.

APPLICATION

Degreasing: Necessary before painting. Rub the supports with a sponge soaked in a degreaser (i.e. R-Clean), rinse and then wipe with absorbent paper.

I. Brush and roller: Hydrogrip should be diluted with 2 to 5% of water.

2. Spray - 2 thin coats

- Nozzle: 1,2 à 1,5

- Pressure: 2 bar on the container

- Dilution : With 10 % of water for an application viscosity of 30 seconds with cup FORD N° 4.

- Wet-film thickness : 110 à 125 my. Dry-film thickness : 70 à 75 my

The ideal processing temperature in the spray booth is between 18°C and 20°C.

In order to accelerate the drying of the paint, the temperature can be increased to 40° C max. Sprayed pieces need to dry at least 30 minutes before increasing the temperature.

DRYING TIME

Dust-free: 15-30 min.

Dry: 2 hours.

Recoverable after 48 hours with solvent-based paints.

PROPERTIES

Dry extract : 59,9 %.Density : 1,29.

- Consumption: 6 to 8 m² / l.

- VOC: 21g/l.

STORAGE CONDITIONS

I year in unopened original container. Store in a ventilated room at a temperature between +5°C and +35°C. Protect from frost.

Our information on the technical product is used only as assistance to professional workers. During the implementation of our products, we always advise to start with a test on a small area.