

LAQUE RB

PRODUCT DESCRIPTION

A durable, breathable, multi-coat satin paint that regulates the humidity of wood and other materials. For exteriors and interiors.

Microporous, RB Lacquer regulates and stabilizes humidity.

Flexible, it resists surface deformation without cracking or blistering.

Multi-coat, it can be used as a primer, intermediate, and finish for woodwork, depending on its dilution. Its flexibility provides increased longevity.

Opacifying, it stands out on most surfaces for its high opacity and excellent edge coverage.

DESTINATION

Opacifying primer, intermediate, and finish, particularly suitable for new woodwork that has not yet eliminated excess internal moisture.

Also suitable for maintenance work, as a primer and finish on woodwork, and as a finish on metal and wall surfaces with appropriate primers.

FEATURES

- Dilution with white spirit.
- Drying time:
 - Dust-free: 2 to 3 hours.
 - Dry: 5 to 6 hours.
 - Hard: 24 hours.
- Coverage: $10 \text{ to } 12 \text{ } \text{m}^2\text{/l}$ depending on the porosity of the substrate.
- Brushability: Very good. Perfect roundness.
- Washability: Excellent.
- Opacity: Very good, even on edges.
- Cleans fresh paint: With white spirit.
- Storage: Excellent adhesion.
- Density: 1.24.
- Solids by weight: 62.94%.
- VOC: EU limit values for this product (cat. IIA/d): 400g/I (2007). RB Lacquer contains 353g/I of VOC.

INSTRUCTIONS FOR USE

Equipment: Brush, roller, airbrush, or airless spray gun (nozzle 1.2-1.5).

Application: After normal surface preparation, and for woodwork: For new wood, lightly sand and dust (exotic woods must be degreased). For painted wood, sand and degrease or strip. For other materials, apply like a conventional enamel.

Dilution: RB Lacquer should be applied as a primer at a 5-10% dilution with white spirit, as is, as an intermediate and finishing coat.

Nos informations sur les produits et les recommandations techniques servent d'assistance aux travailleurs professionnels. Lors de la mise en œuvre, nous conseillons toujours de commencer par un essai.