



LEVASSEUR
Your paint expert

TOPTEX RP

PRODUCT DESCRIPTION

Self-cleaning facade paint.

This product can also be applied indoors to ensure optimal washability of the substrate to which it is applied. Facade paint for existing acrylic, silicate, or pliolite coatings and new substrates: cement, brick, and limestone.

Appearance: Deep matte.

COMPOSITION

Acrylic copolymer and siloxane resin.

PROPERTIES

Density: 1.5

Viscosity: 6,500 CP, HAAKE Rotor No. 1 Viscometer

Silicone resin, hydrophobic system.

Very good beading effect.

Rapid elimination of rainwater, which carries away loose dust.

Excellent weather resistance and resistance to microorganisms.

Odorless.

Excellent water vapor permeability.

Sd = 0.03.

Excellent water impermeability

W = 0.08 (kg/m² h^{1/2}).

Excellent UV resistance

Class 2 wet rubbing resistance.

INSTRUCTIONS FOR USE

Ready-to-use product.

Excellent brushability and roller application.

Application by brush, roller, or spray gun.

Toptex RP is applied in two coats with a maximum dilution of 5% water.

Old surfaces must be freed of all dirt.

Loose areas must be removed.

Salt efflorescence must be brushed off.

Surfaces contaminated by fungi and mold must be treated with Antimousse NM (see technical data sheet for use).

Metal parts must be insulated with a suitable primer.

New and chalky surfaces must be primed with the ready-to-use Toptex RP Primer.

In case of high absorption of the surface, we recommend applying Toptex RP Primer to saturation.

On old acrylic or silicate paints, we recommend diluting the first coat with 10% water.

S.A. LEVASSEUR NEWCO N.V.

Rue du Bourdon - 121 - Horzelstraat - B - 1180 BRUXELLES - BRUSSEL
Tel. 02/ 376 00 18 - Fax. 02/ 376 38 86 - info@g-levasseur.com - www.levasseur.be



LEVASSEUR
Your paint expert

CONDITIONS TERMS OF USE

Do not apply in direct sunlight or when the temperature is below +5°C.
Ideal application temperatures: between +10°C and +30°C, outdoor temperatures.
Be careful, adverse reactions may occur outside these temperatures.

FEATURES

Drying: 4 hours at 20°C, MR 60%
Recoat after 4 hours.
Coverage: 6–8 m²/litre.
VOC: EU limit values for this product (Cat. IIA/c): 40g/l (2010). The current value is 0g/l.

CLEANING

In the water.

STORAGE CONDITIONS

Storage: 1 year in original unopened packaging and stored away from frost.

Our information on the technical product is used only as assistance to professional workers. During the implementation of our products, we always advise to start with a test on a small area.

S.A. LEVASSEUR NEWCO N.V.

Rue du Bourdon - 121 - Horzelstraat - B - 1180 BRUXELLES - BRUSSEL
Tel. 02/ 376 00 18 – Fax. 02/ 376 38 86 – info@g-levasseur.com – www.levasseur.be