



LEVASSEUR
Your paint expert

EASY COLOR DECO GOLD

GOLD 906 COPPER 907 SILVER 908

PRODUCT DESCRIPTION

Water borne paint for wall application.

PROPERTIES

Water borne product : odorless, free using, no plastifier, no cosolvent.
Good opacity.
Regular penetration on substrate.
Regular drying.
Easy to clean.
Good washability.

APPLICATION

Support must be clean and properly prepared as mentioned in DIN 18363 Teil c.

New ground :

At least 28 days of drying for plaster and concrete.

- Take off grease, dust and clean well.
- Repair cracks with appropriate coating.
- Treat metal parts with a primer.
- Tannic wood needs to be treated with isolated primer.
- Chalky surface needs to be treated with a fixator primer.

Old ground :

After preparation : same as new ground.

- Take off all non-adherent parts. If a washing is done with high pressure, support has to be totally dry.
- Chalky surface needs to be treated with a fixator primer.

APPLICATION ENVIRONMENT

Temperature has to be between 10°C and 30°C.

Higher temperature could have a significant influence on drying time.

Humidity level <80 %.

SURFACE PREPARATION

New walls or painted walls, clean and without any chalky problem.

- Direct application : Walls, ceilings, plaster, plaster with cardboard, brick, cement, concrete, wall paper, plaster moulding.
- After support preparation : wood, compressed wood, metal ferrous and non ferrous.

S.A. LEVASSEUR NEWCO N.V.

Rue du Bourdon - 121 - Horzelstraat - B - 1180 BRUXELLES - BRUSSEL
Tel. 02/ 376 00 18 - Fax. 02/ 376 38 86 - info@g-levasseur.com - www.levasseur.be



LEVASSEUR
Your paint expert

CARACTERISTIQUES

Composition : Binder : aqueous polymer (VAE).
Colors : Glossy gold, copper or silver.
Aspect : Thixotropic.
Density : 1,13 +/- 0,05 kg/L.
Viscosity at 20°C : 1500 +/-200mPas HAAKE VTOR2.
Application : Brush, rol, low pressure gunspray.
Dry film aspect : Satin following ISO 2813, RHOPOINT 60°C.
Washability : Class 2 following ISO 11998.
pH : 8.5 +/-0.2.
Coverage : 8-11 m²/L on clean support without any loss.

CLEANING OF MATERIAL

Water.

DRYING TIME (20°C AND 60% HR)

Touch free : 1 hour.
Recoatible : 4 hours.

STORAGE CONDITIONS

1 year in closed sealed cans.
Stock in a ventilated area with temperature between 5°C and 30°C.

Our information on the technical product is used only as assistance to professional workers. During the implementation of our products, we always advise to start with a test on a small area.

S.A. LEVASSEUR NEWCO N.V.

Rue du Bourdon - 121 - Horzelstraat - B - 1180 BRUXELLES - BRUSSEL
Tel. 02/ 376 00 18 - Fax. 02/ 376 38 86 - info@g-levasseur.com - www.levasseur.be