

# EASY COLOR DECO PLATINUM 915

# **PRODUCT DESCRIPTION**

Water borne paint for wall application - Platinum effect.

## PROPERTIES

Water borne product : odorless, free using, no plastifier, no cosolvant. Good opacity. Regular penetration on substrate. Regular drying. Easy to clean. Good washability.

#### APPLICATION

Support must be clean and properly prepared as mentioned in DIN 18363 Teil c. **New ground :** 

At least 28 days of drying for plaster and concrete.

- Take off grease, dust and clean well.
- Repair cracks with appropriate coating.
- Treat metal parts with a primer.
- Tannic wood needs to be treatred with isolated primer.
- Chalky surface needs to be treated with a fixator primer.

#### Old ground :

After preparation : same as new ground.

- Take off all non-adherent parts. If a washing is done with high pressure, support has to be totally dry.
- Chalky surface needs to be treated with a fixator primer.

## **APPLICATION ENVIRONMENT**

Temperature has to be between  $10^{\circ}$ C and  $30^{\circ}$ C. Higher temperature could have a significant influence on drying time. Humidity level <80 %.

#### SURFACE PREPARATION

New walls or painted walls, clean and without any chalky problem.

- Direct application : Walls, ceilings, plaster, gypsum boards, cement, wall paper.
- After support preparation : wood, compressed wood, metal ferrous and non ferrous.



# CARACTERISTIQUES

Composition : Binder : Aqueous polymer. Aspect : Thixotropic. Application : Low pressure gunspray or airless. Coverage : 8-11 m<sup>2</sup>/L on clean support without any loss.

## **CLEANING OF MATERIAL**

Water.

## DRYING TIME (20°C AND 60% HR)

Touch free : I hour. Recoatable : 4 hours.

## **STORAGE CONDITIONS**

I year in closed sealed cans. Stock in a ventilated area with temperature between  $5^{\circ}$ C and  $30^{\circ}$ C.

Our information on the technical product is used only as assistance to professional workers. During the implementation of our products, we always advise to start with a test on a small area.